# MADEIRA Technical Datasheet

11.09.2019

4-5

# **BURMILON No. 200**

Article Description	Bobbin Thread
Composition	100% polyester
Count	150 dtex x 1 / 135 den x 1
Make Up Available	7.500m cone

Fastness to washing at 95°C	DIN EN ISO 105-C04/M & S C4A	4-5
Fastness to water (damp for 4hrs at 37°C)	DIN EN ISO 105-E01/M & S C6	4-5
Fastness to rubbing dry (10 rubs on dry white Fabric)	DIN EN ISO 105-X12/M & S C8	4
Fastness to rubbing wet (10 rubs on wet white Fabric)	DIN EN ISO 105-X12/M & S C8	3-4
Fastness to dry cleaning	DIN EN ISO 105-D01	4-5

Determination of the colourfastness of articles for common use – Part 1: Test with artificial saliva

DIN 53160-1

Determination of the colourfastness of articles for common use – Part 2: Test with artificial sweat

4-5

### Fastness Rating - Scale 1 (worst) - 8 (best)

Fastness to bleaching with Hypochlorite

Fastness Rating - Scale 1 (worst) - 5 (best)

Fastness to light (100hrs xenon light)

DIN EN ISO 105-B02

6-7

Due to different dye stuffs not applicable to all colors.

# Mechanical – Technological Values

Tensile Strength cN (force until thread breaks, in Centinewton) DIN EN ISO 2062 ca.480cN Elongation (% of stretch extension with weight tension until breaks) DIN EN ISO 2062 ca.14% Shrinkage (shrinkage at boiling water) DIN 53866 T2 < 1 %

## **Recommendations for care**



∆max. 20g/l active chlorine- max. 30°C - max. 30 min

### **Oeko-Tex**



DIN EN ISO 105-N01/M & S C10A

DIN 53160-2

To improve this product Madeira reserves the right to alter the specifications or modify the appearance of products without notice. Information and technical data in this document are guidelines and no warranted characteristics. Small variations due to production process are possible.

MADEIRA Garnfabrik Rudolf Schmidt KG Zinkmattenstraße 38 D-79108 Freiburg

Tel.: +49 (0) 761 – 51 04 00 E-Mail: service@madeira.de

